



Technical Data Sheet

Product Name: Potterycrafts Basalt Fleck Clay

Product Number: P1552

Product profile:

Firing Range: 1120°C -1280°C

Colour: Warm Buff

Texture: Coarse

Bag Size: 10kg

Linear shrinkage: Moisture content 19.25%

Dry to fired (1260° C) : 13.4%

Chemical Analysis %	
Chemical	Percentage
Sio2	62.52
Tio2	1.13
AL2O3	22.39
Fe2O3	2.59
P2O3	0.05
CaO	0.35
MgO	0.79
K2O	2.18
Na2O	0.20

Coefficient of Thermal Expansion [1260 °C]

$$\alpha_{20-500} = 5.46 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$$

0.262 % @ 500° C

An addition of 2.5% Basalt Fleck of various grain sizes is blended into the plastic clay.

Uses: Throwing, Modelling and Hand building.

Footnote

LIABILITY

Such information is the best of Potterycrafts Ltd's knowledge and belief accurate at the date of publication, which is the date generated automatically on the day of printing of this document. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy itself as to the suitability and completeness of such information for their own particular use.

THIRD PARTY MATERIALS

Insofar as materials not manufactured or supplied by Potterycrafts Ltd are used in conjunction with, or instead of Potterycrafts Ltd materials, it is the responsibility of the customer itself to obtain from the manufacturer or supplier all technical data and other properties relating to these and other materials and to obtain all necessary information relating to them. No liability can be accepted in respect of the use of Potterycrafts Ltd materials in conjunctions with other materials.